

# Certificate of Technical Specifications

**portinari**

ambientes com emoção

PRODUCT: YORK DECOR SGR MATTE  
 FORMAT: 291.0 X 1170.0mm X 10.0 mm

CONTAINS: 4 Peças 1,36 m2 14,64 SQFT


GROUP: Bla

Technical Characteristics	ISO	Req.	Unit	Specification
DIM. VAR. IN REL. W. OF THE GREATER SIDE	10545-2	±1.0	mm	±1.0
DIM. VAR. IN REL. W. OF THE MINOR SIDE	10545-2	±0.80	mm	±0.80
THICKNESS VARIATION	10545-2	±0.50	mm	±0.50
STRAIGHTNESS OF THE GREATER SIDE	10545-2	±0.80	mm	±0.80
STRAIGHTNESS OF THE MINOR SIDE	10545-2	±0.80	mm	±0.80
DEVIATION FROM ORTHOGONALITY OF THE GREATER SIDE	10545-2	±1.50	mm	±1.50
DEVIATION FROM ORTHOGONALITY OF THE MINOR SIDE	10545-2	±0.87	mm	±0.87
CENTRAL DIAGONAL CURVATURE DEVIATION	10545-2	±1.80	mm	±1.80
DEVIATION OF THE CURVATURE OF THE SIDES	10545-2	±1.80	mm	±1.80
DEVIATION OF THE CURVATURE OF THE SIDES	10545-2	±1.16	mm	±1.16
BENDING OVER DIAGONAL	10545-2	±1.80	mm	±1.80
QUALITY OF SURFACE	10545-2	≥95	%	≥95
WATER ABSORPTION	10545-3	≤0.5	%	≤0.5
RESISTANCE TO BENDING	10545-4	≥35	N/mm2	≥35
BREAKING STRENGTH	10545-4	≥1300	N	≥1300
CLASS OF USAGE			USO:	2
THERMAL SHOCK RESISTANCE	10545-9	-	-	-
LINEAR EXPANSION COEFFICIENT X 10-6	10545-8	-	°C-1	-
MOISTURE EXPANSION	10545-10	-	mm/m	≤0.30
GRAZING RESISTANCE	10545-11	-	-	OK
RESISTANCE TO CHEMICALS	10545-13	Minimum Class GB	-	GA
RESISTANCE ATTACKS ACID/ALKALINE	10545-13	Specify	-	GLB
SURFACE RESISTANCE TO STAINS	10545-14	Minimum Class 3	-	Min.Class 3
COEFFICIENT OF FRICTION WET	NBR16919	Specify		-
CHANGES IN HUE				V2

Note: Product in accordance with ABNT NBR 13006 standard

Reaction to fire evaluation (NBR15575): Class I (non-combustible)

USE 2 - Use on internal and external walls.

  
 Jamilson Pinter Júnior  
 Responsável Técnico RC1 e RC2

  
 Galdino da Luz  
 Responsável Técnico RC3 e RC4